

“Rizokon™ Sport Coating 1S”

Sport Flooring Based on Rubber Granules

Application: Economic-class flooring. It is applied for out-doors playgrounds, gyms.
It provides reliable traction and high safety.
Sport painted coating based on rubber granules

№	Usage	Material	Consumption Kg/m ²		Tool Mode
1.	Primer	Rizopox™ – 1100 or Rizopur™ – 1700	0.3 ÷ 0.4		Solvent resistant roller, Pile height is 15 – 18 mm
2.	Strengthening layer	Rizopur™ – 1731	0.98		By hand using metal trowel
		Rubber granules 1-4 mm	6.9		
3.	Front/face layer	Rizopur - 5615 W	0.25 2 layers		Solvent resistant roller, Pile height is 8 – 12 mm
	Total				

Total thickness: 10 mm

Sport Flooring Based on Rubber Granules and “Coler™-PU”

№	Usage	Material	Consumption Kg/m ²		Tool Mode
1.	Primer	Rizopox™ – 1100 or Rizopur™ – 1700	0.3 ÷ 0.4		Solvent resistant roller, Pile height is 15 – 18 mm
2.	Front/face layer	Rizopur - 1731	0.98		By hand using metal trowel
		Rubber granules 1-4 mm	6.9		
		“Coler™-PU”	0.25*		
	Total				

Total thickness: 10 mm

Notes:

* - “Coler™-PU” 20-25% of “Rizopur™- 1731”

When choosing flooring it is necessary to take into account all data. Address your requests to the Manufacturer.